



Mixing Ratio	50-53 ml /100 gr
Mixing Time by Hand / Mixer	60" / 30"
Working Time	4'
Final Setting Time (Vicat)	7'
Demoulding time	n.a.
Setting Expansion (2 h)	< 0.28%
Compressive strength (1h)	> 10 MPa

Alabaster plaster with exceptional workability and easy handling.

**ALABASTER ROCK** can be used in various stages of the orthodontic process.

CODE	PACKAGING
<b>DALS25 WT</b>	Light brown paper bag 55.12 lbs

Standard color: **WT**= Natural white

Color customization is available upon request.