



Mixing ratio	20-21 ml /100 gr
Mixing time by hand/Mixer	60" / 30"
Working time	9'
Final setting time (Vicat)	13'
Demoulding time	45'
Setting Expansion (2 h)	< 0.08%
Compression Streight (1 h)	> 45 MPa

This type IV extra hard plaster is highly thixotropic, precise in the reproduction of every detail, resistant to abrasion, and has a low setting expansion. These qualities make **CARVER ROCK** an essential ally for the production of any kind of model and abutments for fixed dentures, both partial and total.

CODE	PACKAGING
<b>DGR20 GB/BG</b>	Rectangular plastic drum kg 20
<b>DGRC10 GB/BG</b>	Box kg 10=10 1kg bags
<b>DGR5 GB/BG</b>	Conic plastic drum kg 5

Standard color: **GB**= Golden brown **BG**= Blue gray

Color customization is available upon request.



[www.regeco.it](http://www.regeco.it)  
+39 0131 217398