



Mixing Ratio	27-28 ml /100 gr - 0.22 lbs
Mixing Time by Hand / Mixer	60" / 30"
Working Time	7'
Final Setting Time (Vicat)	9'
Demoulding Time	35'
Setting Expansion (2 h)	< 0.18%
Compressive strength (1h)	> 30 MPa

High quality hard plaster (type III) that allows for smooth, compact surfaces and strong resistance.

**FULLROCK** is ideal for the manufacturing of models for total and partial dentures as well as any other model.

CODE	PACKAGING
DGFS25 YE/BL/PK/WT	White paper bag kg 25
DGF20 YE/BL/PK/WT	Rectangular plastic drum kg 20
DGF25 YE/BL/PK/WT	Conic plastic drum kg 25

Standard color: **YE**= Yellow **BL**= Blue **PK**= Pink **WT**= Natural white

Color customization is available upon request.