



Mixing Ratio	29-31 ml /100 gr
Mixing Time by Hand / Mixer	60" / 30"
Working Time	8'
Final Setting Time (Vicat)	10'
Demoulding Time	35'
Setting Expansion (2 h)	< 0.20%
Compressive strength (1h)	> 20 MPa

EASYROCK (type III) is a versatile plaster with a wide range of uses. It has a high capability of reproducing the impression material and excellent handling properties.

Suitable for the development of models for partial, total and fixed provisory dentures, and for the creation of flasking work.

CODE	PACKAGING
DGES25 DY	White paper bag kg 25
DGE20 DY	Rectangular plastic drum kg 20

Standard color: **DY**= Dark yellow

Color customization is available upon request.