



Mixing Ratio	32-33 ml /100 gr - 0.22 lbs
Mixing Time by Hand / Mixer	30" / ---
Working Time	2'
Final Setting Time (Vicat)	4'
Demoulding Time	35'
Setting Expansion (2 h)	< 0.08%
Compressive strength (1h)	> 18 MPa

High precision, optimal workability and the extremely reduced setting expansion are the characteristics that make **FAST ROCK** the ideal plaster for the positioning of models on articulators.

CODE	PACKAGING
DGT20 WT	Rectangular plastic drum kg 20
DGT25 WT	Conic plastic drum kg 25

Standard color: **WT**= Natural white

Color customization is available upon request.