



Mixing ratio	22-23 ml /100 gr
Mixing time by hand/Mixer	30" / --
Working time	3'
Final setting time (Vicat)	5'
Demoulding time	15'
Setting Expansion (2 h)	< 0.15%
Compression Strenght (1 h)	> 35 MPa

Technical plaster, special hard plaster (type IV), is fluid and precise in addition to having a fast setting time.

FLASH ROCK allows, where needed, for fast setting model with rapid demoulding, enabling the immediate analysis of clinical cases.

CODE	PACKAGING
DGH20 LG	Rectangular plastic drum kg 20
DGH5 LG	Conic plastic drum kg 5

Standard color: **LG**= Light green

Color customization is available upon request.



www.regeco.it
+39 0131 217398