



Mixing ratio	25-26 ml /100 gr
Mixing time by hand/Mixer	60" / 30"
Working time	7'
Final setting time (Vicat)	9'
Demoulding time	n.a.
Setting Expansion (2 h)	< 0.08%
Compression Strenght (1 h)	> 35 MPa

Extremely fluid type IV plaster, created specifically for making bases when using the removable die technique. The ideal fluidity, together with a longer processing time, allows for the simultaneous production of more bases as well as obtaining a perfectly smooth surface without the use of a vibrating plate. Very low expansion values, elevated hardness and precision all make **FLUID ROCK** the ideal plaster for working models bases.

CODE	PACKAGING
<b>DGL20 DB</b>	Rectangular plastic drum kg 20
<b>DGL5 DB</b>	Conic plastic drum kg 5

Standard color: **DB**= Denim Blue

Color customization is available upon request.



[www.regeco.it](http://www.regeco.it)  
+39 0131 217398