



Mixing Ratio	24 ml /100 gr
Manual Mixing Time	30"
Working Time	5/6'
Final Setting Time	8'
Thermal Expansion at 700°C	1%
Melting Point	850°C
Mixing Ratio	24 ml /100 gr

Investment created for all kinds of soldering with a fast setting and hardening time and an optimal expansion control.

CODE	PACKAGING
DRT20 WT	Rectangular plastic drum kg 20
DRT5 WT	Conic plastic drum kg 5

Standard color: **WT**= Natural white

Color customization is available upon request.